



WELDING PROCEDURE SPECIFICATION

WPS: 5000-xxxx-HY80/HSLA100-IX

REV. NO.: 1

DATE: 7/3/2012

APPLICABILITY

WELDING PROCESS: SAW

CODE: ASME IX

OTHER:

SUPPORTING PQR: 5000-HY80/HSLA100

JOINT: This WPS shall be used in conjunction with the General Welding Standards (GWS) and Welding Fabrication Procedure (WFP) sections and criteria for joint details, repairs, NDE, inspection, etc.

Weld Joint Type: Butt/Fillet

Class: Full & Partial Penetration & Fillets

See GWS 1-06 and WFP's for joint details.

Preparation: Thermal or Mechanical

Root Opening: N/A

Backing: Metal

Backgrind Root: When required

Backing Mat.: Metal

Bkgrd Method: Gouge, Chip, Grind

GTAW Flux: N/A

Backing Retainer: N/A

FILLER METALS:

Class: Mill-100S-1 and N/A

A No: N/A

SFA Class: N/A and N/A

F No: N/A and N/A

Size: .045 1/16 3/32 1/8

Insert: N/A

Insert Type: N/A

Weld Metal Thickness Ranges:

Flux: Type: Mil800-H

Size: N/A

AWS Root Pass: 0 thru 0

Filler Material Note:

AWS Balance: 0 thru 0

ASME Root Pass: .125 thru .250

ASME Balance: .1875 thru 8

BASE MATERIAL:

P No: N/A

Gr No.: N/A

to P No.: N/A

Gr No.: N/A

Spec.: HY80 or HSLA100

Grade: N/A

to Spec.: HY80 or HSLA100

Grade: N/A

Qualified Pipe Dia. Range: >=

AWS: 0

ASME: 2.5

Qualified Thickness Range:

AWS: 0 thru 0

ASME: 0.1875 thru 8

QUALIFIED POSITIONS:

AWS: N/A

ASME: 1G

Vert. Prog.: N/A

Preheat Min. Temp.: 200

GAS: Shielding: N/A or N/A

Interpass Max. Temp.: 400 °F

Gas Composition: N/A / N/A / N/A % N/A / N/A / N/A %

Preheat Maintenance: 200 °F

Gas Flow Rate cfh: 0 to 0

0 to 0

PWHT: Time @ °F Temp.: N/A

Backing Gas/Comp: N/A

N/A %

Temperature Range: N/A °F to N/A °F

Backing Gas Flow cfh: 0 to 0

Trailing Gas/Comp: N/A

N/A %

WELDING CHARACTERISTICS:

Current: DCEN

Tungsten Type: N/A

Transfer Mode: N/A

Ranges: Amps: 200

Tungsten Dia.: N/A

Pulsing Cycle: N/A to N/A

Volts: 18

Background Current: N/A

Fuel Gas: N/A

Flame: N/A

Braze Temp °F: N/A to N/A

WELDING TECHNIQUE: For fabrication specific requirements such as fitup, cleaning, grinding, PWHT and inspection criteria, refer to Volume 2, Welding Fabrication Procedures.

Technique: Machine

Cleaning Method: Chip/grind/file/wire brush

Single or Multi Pass: Multi **Stringer or Weave Bead (S/W):** S or N/A **Oscillation:** N/A
GMAW Gun Angle: 0° to 0° **Forehand or Backhand for GMAW:** N/A
No Pass > 1/2": N/A **GMAW/FCAW Tube to Work Distance (in):** N/A
Maximum K/J Heat Input: 62000 KJ/in **Travel Speed:** **Gas Cup Size:** N/A

PROCEDURE QUALIFIED FOR:

Charpy "V" Notch: Yes **Nil-Ductile Transition Temperature:** No **Dynamic Tear:** Yes

Comments: Note 1.) Welds are qualified with DT of weld material @-40° F of 614 ft-lbs. Westmoreland Report #2-64863 Note2.) Welds are qualified with Charpy of weld material @-90° F of 68 ft-lbs. Sherry Labs Report #B12051281

| Weld Layer | Manual Process | Filler Metals | Size | Amp Range | Volt Range | Travel/ipm | Nozzle Angle | Other |
|------------|----------------|---------------|------|------------|------------|------------|--------------|-------|
| 1 | SAW | Mill-100S-1 | .045 | 200 to 240 | 18 to 22 | 2.3 to 3.0 | 0 to 0 | |
| 2 | | N/A | 1/16 | 345 to 390 | 24 to 28 | 8 to 12 | | |
| 3 | | N/A | 3/32 | 340 to 600 | 26 to 34 | 9 to 12 | | |
| 4 | | N/A | 1/8 | 350 to 600 | 26 to 34 | 9 to 12 | | |

REM. * Weld layers are representative only - actual number pf passes and layer sequence may vary.

ML-1/2 projects or jobs must determine if the supporting documentation for this WPS complies with quality requirements of the project/job.

Use of LANL Welding Procedures and Welder Qualifications for non-LANL work shall be at the sole risk and responsibility of the Subcontractor, and the Subcontractor shall indemnify and save LANL and the Government harmless from any and all claims, demands, actions or causes of action, and for any expense or loss by the reason of Subcontractor's and their employees posession and use of LANL procedures and qualifications.

APPROVAL: Signatures on file at ES-DE

DATE: 7/11/2012